

S. Kerli<sup>1</sup>, Ü. Alver<sup>2</sup>, M. Gögebakan<sup>3</sup>

## **Investigation of The Effect of Annealing on Resistivity in Aluminum-based Amorphous Alloys**

<sup>1</sup>*Energy System Engineering Department, Kahramanmaraş İstiklal University, Kahramanmaraş, Turkey, [suleymankerli@yahoo.com](mailto:suleymankerli@yahoo.com)*

<sup>2</sup>*Department of Metallurgical and Materials Engineering, Karadeniz Technical University, Trabzon, Turkey*

<sup>3</sup>*Department of Physics, Faculty of Science and Letter, Kahramanmaraş Sutcu Imam University, Turkey*

In this study, electrical properties of Al-Y-Ni alloys produced by melt-spinning method were investigated. Before annealing, XRD analyzes were performed and the samples were found to be amorphous. Exothermic peaks were observed in DSC measurements and crystallization stages of the alloys were determined. Al<sub>85</sub>Y<sub>11</sub>Ni<sub>4</sub>, Al<sub>85</sub>Y<sub>10</sub>Ni<sub>5</sub> and Al<sub>85</sub>Y<sub>5</sub>Ni<sub>10</sub> samples were annealed at some temperature and their electrical resistivities were measured by four-point method. The large decrease in resistivity was observed during crystallization between 200-400 °C. These results were consistent with XRD and DSC measurements.

**Keywords:** amorphous alloy, crystallization, electrical resistivity.

*Стаття постулила до редакції 21.11.2019; прийнята до друку 15.12.2019.*

### **Introduction**

The most important feature that distinguishes amorphous alloys or metallic glasses from other alloys is that they do not have the atomic order of normal crystals and consequently do not have crystal structure. This structural and chemical state is felt in all properties and behaviors of metallic glasses, especially mechanical, chemical and electrical-magnetic. Scientists' work on amorphous alloys is quite intense [1-10]. Some properties of Al-Y-Ni alloy which is one of amorphous alloys were investigated. some of those; Chang et al, Al<sub>85</sub>Ni<sub>5</sub>Y<sub>10</sub>, Al<sub>85</sub>Ni<sub>7</sub>Y<sub>8</sub> and Al<sub>85</sub>Ni<sub>10</sub>Y<sub>5</sub> amorphous alloys produced by melt-spinning method. They determined phase transition temperatures by DSC measurements, annealed at these temperatures and made their X-ray analysis. They also examined in detail how the effect of ratios in alloys and the speed of the disc affect the amorphous structure [11]. Freitag et al., Al<sub>85</sub>Y<sub>x</sub>Ni<sub>15-x</sub> (x = 3 - 12 at.%) amorphous alloys, investigated the effect of aluminum (Al) and yttrium (Y) on resistivity at room temperature [12]. Pekala, Al<sub>85</sub>Y<sub>10</sub>TM (TM = Cu,

Ni, Co, Fe) amorphous alloys produced by melt spinning method, determined the effect of metal atoms on electron-photon interaction and examined thermoelectric power at temperatures between 20 - 300 K [13]. Again, Pekala explained the thermoelectric power and electrical resistivity of Al<sub>90-x</sub>Y<sub>10</sub>Ni<sub>x</sub> (x = 0, 2, 5, 8) amorphous alloys by Faber-Ziman theory. He measured the resistivity of these alloys at temperatures between 300 - 800 K by four-point method. He also examined and

**Table 1**  
Production parameters of used alloys

Samples	Crucible hole diameter (mm)	Production speed V(m/s)	Sample thickness W (µm)
Al <sub>85</sub> Y <sub>11</sub> Ni <sub>4</sub>	1.0-1.2	50-60	≈ 25-30
Al <sub>85</sub> Y <sub>10</sub> Ni <sub>5</sub>	0.9-1.2	50-60	≈ 25-30
Al <sub>85</sub> Y <sub>5</sub> Ni <sub>10</sub>	0.9-1.0	30-50	≈ 40-50

compared the thermoelectric strength of these alloys in their crystalline and amorphous state [14]. Gögebakan,  $\text{Al}_{85}\text{Y}_{11}\text{Ni}_4$ ,  $\text{Al}_{85}\text{Y}_{10}\text{Ni}_5$ ,  $\text{Al}_{85}\text{Y}_8\text{Ni}_7$ ,  $\text{Al}_{85}\text{Y}_5\text{Ni}_{10}$  and  $\text{Al}_{85}\text{Y}_2\text{Ni}_{13}$  alloys produced by melt spinning method, examined the mechanical properties, tensile strength ( $\sigma_f$ ), Young's modulus ( $E$ ) and Vickers hardness ( $H_v$ ) measured and compared alloys [15]. Vasiliev et al., ( $\text{Al}-2.6\text{Y}-9.5\text{Ni}$ ), ( $\text{Al}-4.5\text{Y}-10.1\text{Ni}$ ), ( $\text{Al}-4.3\text{Y}-3.5\text{Ni}$ ) and ( $\text{Al}-1.7\text{Y}-6.4\text{Ni}$ ) in atomic ratios of amorphous alloys, with electron microscopy (TEM) investigated the morphology and crystal structure of each phase. In each alloy group, they have observed the formation of  $\alpha\text{-Al}$ ,  $\text{Al}_3\text{Ni}$  or  $\text{Al}_3\text{Y}$  and a triple phase [16]. Min Young Na. et al. conducted research on thermoplastic formability and electrical conductivity in  $\text{Al-Ni-Y}$  metallic glasses [17]. In this study, electrical properties of  $\text{Al-Y-Ni}$  amorphous alloys were investigated.

## I. Experimental

Samples used in this study were produced by melt-spinning technique. Production parameters of the alloys used are given in Table 1 [18].

DSC (Differential scanning calorimetry) was measured by Perkin Elmer Sapphire. X-ray diffraction analysis, Rigaku D/max-IIIIC diffractometer using  $\text{CuK}\alpha$  ( $\lambda = 1,542 \text{ \AA}$ ) radiation. Measurements were carried out at room temperature in the range of  $20 \leq 2\theta \leq 90$  with  $0.02^\circ$  steps.

Electrical measurements were made by Lucas Pro 4 device using four probe method. Here, the samples were




Fig. 1. DSC analysis results of samples.

annealed at some temperatures (not in situ), measured several times and averaged.

## II. Results and discussion

Differential Scanning Calorimetry (DSC) peak patterns for  $\text{Al}_{85}\text{Y}_5\text{Ni}_{10}$ ,  $\text{Al}_{85}\text{Y}_{10}\text{Ni}_5$  and  $\text{Al}_{85}\text{Y}_{11}\text{Ni}_4$  samples are shown in Figure 1. In the DSC analysis by continuous heating, three exothermic peaks were observed for the alloys used. Figure 1 shows the crystallization temperatures  $T_x$  and crystallization peaks  $T_1$ ,  $T_2$ ,  $T_3$  of the samples. As can be seen from the figure, the crystallization temperature  $T_x$  increased with increasing amount of Y in the alloy. In X-ray diffraction analysis of samples before heat treatment, as can be seen from Figure 2, it is generally of amorphous structure.

One of the amorphous alloys ( $\text{Al}_{85}\text{Y}_5\text{Ni}_{10}$ ) was annealed at certain temperatures and detailed XRD




Fig. 2. X-ray analysis of samples.

measurements were taken. In Figure 3 shows the X-ray diffraction patterns of the  $\text{Al}_{85}\text{Y}_5\text{Ni}_{10}$  sample to before annealing and annealing at  $250^\circ\text{C}$ ,  $355^\circ\text{C}$  and  $390^\circ\text{C}$ . The minimum annealing time was set 15 minutes for each temperature. As can be seen from the figure, the diffraction pattern of the alloy before heat treatment shows a extensive peak in conformity with the amorphous structure. Samples were annealed at peak temperatures of crystallization taking DSC measurements into consideration.

It is seen that the amorphous sample annealed at  $T_1 = 250^\circ\text{C}$  starts to crystallize to give crystal aluminum peaks. It is observed that the alloy continues to crystallize around  $T_2 = 355^\circ\text{C}$  annealing temperature and the structure generally consists of  $\text{Al}$  and  $\text{Al}_3\text{Y}$  phases. At an annealing temperature of  $T_3 = 390^\circ\text{C}$ , the structure is completely crystallized and generally consists of phases  $\text{Al}_3\text{Y}$  and  $\text{Al}_3\text{Ni}$ .

The samples were annealed for 15 minutes at some




Fig. 3. X-ray diffraction patterns of some annealing temperatures of  $Al_{85}Y_5Ni_{10}$  alloy.




Fig. 4.  $\rho/\rho_0$  versus temperature.

temperature values between 25 °C and 600 °C and their resistivities were measured by four-point method at room temperature. It was observed that the resistivity of the samples decreased significantly at the temperature between which the samples started to crystallize ( $T_x$ ) and completely crystallized ( $T_3$ ).

Figure 4 shows the temperature-dependent resistivity of the  $Al_{85}Y_{11}Ni_4$  alloy between 25 °C and 600 °C. In the DSC analysis shown in Figure 1, it was observed that the resistivity of the sample started to decrease at the temperature at which crystallization started ( $T_x \approx 245$  °C). The large drop in resistivity continued until the  $T_3 \approx 400$  °C temperature, where the sample

completely crystallized.

In the  $Al_{85}Y_{10}Ni_5$  alloy, the resistivity of the sample started to decrease at the temperature ( $T_x \approx 240$  °C) at which the crystallization started in the DSC analysis shown in Figure 1. The large drop in resistivity continued until the  $T_3 \approx 360$  °C, where the sample completely crystallized. Again in the  $Al_{85}Y_5Ni_{10}$  sample, the resistivity of the sample began to decrease at the temperature ( $T_x \approx 190$  °C) at which the crystallization started in the DSC analysis shown in Figure 1. The large drop in resistivity continued until the  $T_3 \approx 350$  °C, where the sample completely crystallized. The reason why the resistivity drops in this way can be explained by the

transition of the semi-stable amorphous alloys to the stable (crystal) structure. In addition, it is observed that the resistivity continues to decrease a little with the increasing of annealing temperature of the crystallized samples. This is thought to be related to the reduction of grain boundaries as a result of the growth of the particles in the alloy at high annealing temperatures. There are similar studies aluminum-based amorphous alloys and our results are compatible with them [14, 19-24]. In all alloys, a great decrease in resistivity is observed when it changes from amorphous structure to crystal structure.

## Conclusion

In this study, electrical properties of Al-Y-Ni alloys

previously obtained by melt-spinning method were investigated. The resistivity of the samples were measured by using four point technique at room temperature and annealing at some temperatures between 25°C and 600°C. X-ray analysis showed that the samples were amorphous before annealing. At the peaks obtained by DSC analysis, the crystallization temperatures of the samples were determined to be approximately 200 - 400 °C. A significant decrease in the resistivity of the samples was observed in this temperature range. The reason for the decrease in resistivity in this way can be explained by the transition of the semi-stable amorphous alloys to stable (crystal) structure. It was observed that resistivity increased as Y ratio increased in samples. Similarly, as Ni content decreased, resistance decreased.

- [1] W.K. Jun, R.H. Willens, P.O.L. Duwez, *Nature* 187(4740), 869 (1960) (doi:10.1038/187869b0).
- [2] K. YH, K. Hiraga, A. Inoue, T. Masumoto, *Materials Transactions, JIM*, 35(5), 293 (1994) (<https://doi.org/10.2320/matertrans1989.35.293>).
- [3] A. Inoue, *Acta materialia* 48(1), 279 (2000). ([https://doi.org/10.1016/S1359-6454\(99\)00300-6](https://doi.org/10.1016/S1359-6454(99)00300-6)).
- [4] T.C. Hufnagel, C.A. Schuh, M.L. Falk, *Acta Materialia* 109, 375 (2016) (<https://doi.org/10.1016/j.actamat.2016.01.049>).
- [5] S. Lan, Y. Ren, X.Y. Wei, B. Wang, E.P. Gilbert, T. Shibayama, X.L. Wang, *Nature communications* 8, 14679 (2017) (<https://doi.org/10.1038/ncomms14679>).
- [6] Y. He, P. Yi, M.L. Falk, *Physical review letters*, 122(3), 035501 (2019) (<https://doi.org/10.1103/PhysRevLett.122.035501>).
- [7] F. Zhu, S. Song, K.M. Reddy, A. Hirata, M. Chen, *Nature communications* 9(1), 3965 (2018). (<https://doi.org/10.1038/s41467-018-06476-8>).
- [8] Y. Gao, H. Bei, *Progress in Materials Science* 82, 118 (2016) (<https://doi.org/10.1016/j.pmatsci.2016.05.002>).
- [9] H. W. Bi, A. Inoue, F.F. Han, Y. Han, F.L. Kong, S.L. Zhu, A.L. Greer Novel deformation-induced polymorphic crystallization and softening of Al-based amorphous alloys. *Acta Materialia*, 147, 90-99. (2018) (<https://doi.org/10.1016/j.actamat.2018.01.016>).
- [10] F.G.Cuevas, S. Lozano-Perez, R.M. Aranda, E.S. Caballero, *Intermetallics* 112, 106537 (2019) (<https://doi.org/10.1016/j.intermet.2019.106537>).
- [11] I.T.H. Chang, P. Svec, M. Gogebakan, B. Cantor, *Trans Tech Publications*. 225, 335 (1996) (<https://doi.org/10.4028/www.scientific.net/MSF.225-227.335>).
- [12] J.M. Freitag, Z. Altounian, *Materials Science and Engineering A*, 226, 1053 (1997) ([https://doi.org/10.1016/S0921-5093\(97\)80104-9](https://doi.org/10.1016/S0921-5093(97)80104-9)).
- [13] K. Pekała, *Journal of non-crystalline solids* 250, 800 (1999) ([https://doi.org/10.1016/S0022-3093\(99\)00181-7](https://doi.org/10.1016/S0022-3093(99)00181-7)).
- [14] K. Pekała, *Journal of non-crystalline solids*, 287(1-3), 183 (2001) ([https://doi.org/10.1016/S0022-3093\(01\)00555-5](https://doi.org/10.1016/S0022-3093(01)00555-5)).
- [15] M. Gögebakan, *Journal of Light Metals* 2(4), 271 (2002) ([https://doi.org/10.1016/S1471-5317\(03\)00011-7](https://doi.org/10.1016/S1471-5317(03)00011-7)).
- [16] A.L. Vasiliev, M. Aindow, M.J. Blackburn, T.J. Watson, *Intermetallics* 12(4), 349 (2004) (<https://doi.org/10.1016/j.intermet.2003.11.007>).
- [17] M.Y. Na, S.H. Park, K.C. Kim, W.T. Kim, D.H. Kim, *Metals and Materials International* 24(6), 1256 (2018) (<https://doi.org/10.1007/s12540-018-0130-7>).
- [18] M. Gögebakan, *Amorphous and Nanocrystalline Al-based Alloys*. University of Oxford. Ph.D. thesis, 164s. (1998).
- [19] K. Pekała, (2007). *Journal of Non-Crystalline Solids* 353(8-10), 888 (<https://doi.org/10.1016/j.jnoncrysol.2006.12.094>).
- [20] K.L. Sahoo, A.K. Panda, S. Das, V. Rao, *Materials Letters*, 58(3-4), 316 (2004) ([https://doi.org/10.1016/S0167-577X\(03\)00477-4](https://doi.org/10.1016/S0167-577X(03)00477-4)).
- [21] Ü. Alver, S. Kerli, M. Gögebakan, *Electrical Resistivities and Magnetic Properties of Amorphous Al-Y-Ni Alloys*. In *AIP Conference Proceedings* (899, 1, 614). AIP. (2007). (<https://doi.org/10.1063/1.2733355>).
- [22] V. Sidorov, P. Svec, Sr. P. Svec, D. Janickovic, V. Mikhailov, E. Sidorova, L. Son, *Journal of Magnetism and Magnetic Materials* 408, 35 (2016) (<https://doi.org/10.1016/j.jmmm.2016>).
- [23] R. Raggio, G. Borzone, R. Ferro, *Intermetallics* 8, 247 (2000).
- [24] T. Mika, B. Kotur, *Chem. Met. Alloys* 3, 208 (2010).

С. Керлі<sup>1</sup>, Ю. Алвер<sup>2</sup>, М. Гюгебакан<sup>3</sup>

## Дослідження впливу відпалу на питомий опір аморфних сплавів на основі алюмінію

<sup>1</sup>Кафедра інженерії енергетичних систем, Університет Істклар Кахраманмарасу, Кахраманмарас, Туреччина, [suleymankerli@yahoo.com](mailto:suleymankerli@yahoo.com)

<sup>2</sup>Кафедра металургії та матеріалознавства, Технічний університет Караденізу, Трабзон, Туреччина

<sup>3</sup>Кафедра фізики, Університет Сутку Імама Кахраманмарасу, Туреччина

У статті досліджено електричні властивості сплавів Al-Y-Ni, отриманих методом з розплаву. Перед відпалюванням проведено XRD-аналіз та виявлено аморфність зразків. При DSC-вимірюваннях спостерігалися екзотермічні піки та визначено стадії кристалізації сплавів. Зразки Al<sub>85</sub>Y<sub>11</sub>Ni<sub>4</sub>, Al<sub>85</sub>Y<sub>10</sub>Ni<sub>5</sub> та Al<sub>85</sub>Y<sub>5</sub>Ni<sub>10</sub> при певній відпалювальній температурі, а їх електричний опір вимірювали чотиризондовим методом. Під час кристалізації в інтервалі (200 - 400) °C спостерігається суттєве пониження питомого опору. Ці результати відповідали даним, отриманим із вимірювань XRD та DSC.

**Ключові слова:** аморфний сплав, кристалізація, електричний опір.